

Europäisches Patentamt

European Patent Office

Office européen des brevets



(11) EP 1 273 414 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication: 08.01.2003 Bulletin 2003/02

(21) Application number: 02013230.4

(22) Date of filing: 17.06.2002

(51) Int Cl.⁷: **B29B 17/02**, C08J 11/06, C22B 1/00, C22B 3/00, C22B 7/00

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR
Designated Extension States:

AL LT LV MK RO SI


(30) Priority: 04.07.2001 CN 01122553

(71) Applicant: Chen, Cheng-Shu Talchung Hsien (TW) (72) Inventor: Chen, Cheng-Shu Talchung Hsien (TW)

(74) Representative: Beissel, Jean et al Office Ernest T. Freylinger S.A. 234, route d'Arlon B.P. 48 8001 Strassen (LU)

(54) Method for recycling compact disks

(57) A method for recycling compact disks uses a stripping solution to separate metal from compact disks after smashing the compact disks into pieces. The stripping solution is filtered, and the metal is separated from the stripping solution by absorbents. Then, the absorbents electrolyzed to recover the metal in the absorbents. Other solid residua of the compact disk, plastic pieces, are washed, dried and granulated into plastic particles. Whereby, the compact disks are completely recycled.



25

35

40

Description

1. Field of the Invention

[0001] The present invention relates to a method for recycling compact disks, and more particularly to a method for recycling compact disks to separate the compact disks into separate plastic and metal resources for reprocessing.

2. Description of Related Art

[0002] Compact disks have become a major recording medium in the recording industry. To a significant extent compact disks have replaced the audiotapes or videotapes because the compact disks have a huge memory storage capacity, retain the stored recording longer and provide better quality of sound and picture than the conventional magnetic recording media. Each compact disk is composed of a hard plastic disk and a metal recording layer of aurum, silver or aluminum formed on one side of the plastic disk and is cheap to produce. Although the compact disks retain the stored recording longer than the conventional magnetic recording media, compact disks are easily damaged when the metal layer is scratched, abraded or otherwise damaged to cause gaps or breaks in the memory area on the metal layer. [0003] As compact disks have become more popular and more common, more and more compact disks are inevitably discarded. The discarded compact disks pose a serious environmental problem that is tough to deal with. If the compact disks are discarded without any treatment, the heavy metal in the metal layer leaches into the soil and the water causing pollution to our environment and a potentially serious health hazard. Furthermore, since the plastic and metal in the compact disks are reusable, discarding the compact disks without any treatment is a waste of resources.

[0004] The present invention provides a method for recycling compact disks to obviate the aforementioned problems.

[0005] The main objective of the invention is to provide a method for recycling compact disks to separate the materials used in compact disks into reusable plastic and metal.

[0006] Other objects, advantages and novel features of the invention will become more apparent from the following detailed description when taken in conjunction with the accompanying drawings.

IN THE DRAWINGS

[0007] Fig. 1 is a schematic diagram of a method for recycling compact disks in accordance with the present invention.

[0008] With reference to Fig. 1, a method for recycling compact disks composed of a plastic disk and metal in accordance with the present invention comprises the

following acts.

[0009] Smashing: smashing the compact disks into pieces.

[0010] Adding a stripping solution: the pieces of compact disks are put into a container of stripping solution (reagents for stripping the metal layer from the compact disks) to dissolve the metal in the metal layer from the compact disks into the stripping solution. Residua of the compact disks are plastic pieces suspended in an upper layer of the stripping solution.

[0011] Filtering out the plastic residua: the stripping solution is filtered to separate the plastic pieces from the stripping solution that contains the metal.

[0012] Recycling the metal: the stripping solution containing the metal is mixed with absorbents to undergo an ion exchange reaction to separate the metal from the stripping solution. Then the absorbents are electrolyzed to coat the metal material on a negative electrode to obtain a pure metal. The pure metal is collected, melted and molded into a block of metal. Additionally, the stripping solution after undergoing ion exchange reaction is poured into the container to dissolve the material from additional pieces of the compact disks.

[0013] Recycling the plastic: the plastic pieces are washed with water, dried and then granulated into plastic particles. The water used to wash the pieces of plastic also contains a trace of metal. Therefore, the water is mixed with the absorbents for recycling the metal and then reused.

[0014] Based on the foregoing description of the method for recycling compact disks in accordance with the present invention, the following advantages exist.

- The compact disks are recycled to reduce amount of trash and prevent metal in the compact disks from leaching into and polluting the soil and water in out environment.
- 2. The whole compact disk is recycled into reusable metal and the plastic. All the elements of the compact disks are recovered for reuse.
- 3. The stripping solution and water are also recycled to prevent wasting resources and causing other pollution..

[0015] Even though numerous characteristics and advantages of the present invention have been set forth in the foregoing description, together with details of the structure and function of the invention, the disclosure is illustrative only, and changes may be made in detail, especially in matters of shape, size, and arrangement of parts within the principles of the invention to the full extent indicated by the broad general meaning of the terms in which the appended claims are expressed.

Claims

1. A method for recycling compact disks composed of

2

55

plastic base plates and metal material, the method comprising following acts:

smashing: smashing the compact disks into adding a stripping solution: mixing the pieces of compact disks with a stripping solution to dissolve the metal from the pieces of compact disks into the stripping solution, wherein residua of the compact disks are plastic pieces; filtering out the plastic residua: filtering the stripping solution to separate the plastic pieces and stripping solution containing metal; recycling the metal: mixing the stripping solution containing metal with absorbents to undergo an ion exchange reaction to separate the metal from the stripping solution, the absorbents containing metal are electrolyzed to coat solid metal on a negative electrode; and recycling the plastic: washing the plastic pieces 20 with water, drying and granulating the plastic material into particles.

2. The method for recycling compact disks as claimed in claim 1, wherein the solidified metal is collected, 25 melted and molded into a metal block; and

the stripping solution is reused to remove metal from additional pieces of compact disks.


3. The method for recycling compact disks as claimed 30 in claim 1, the waste water from washing the plastic pieces is mixed with the absorbents for recycling the metal and then reused.

35

45

50

55



EP 1 273 414 A1



EUROPEAN SEARCH REPORT

Application Number EP 02 01 3230

Category	Citation of document with of relevant pas	ndication, where appropriate, sages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.CI.7)
Y	DE 43 24 830 A (LUI 26 January 1995 (19 * column 2, line 24	TER WOLFGANG DIPL ING) 095-01-26) 1-35 *	1-3	B29B17/02 C08J11/06 C22B1/00
Υ	US 4 828 661 A (CEL 9 May 1989 (1989-05 * column 2, line 31	i-09)	1-3	C22B3/00 C22B7/00
Α	US 5 151 452 A (EHL 29 September 1992 (* example 2 *	ERT MANFRED ET AL) 1992-09-29)	1-3	
А	DE 43 06 348 A (SPI 25 August 1994 (199 * column 1-3 *		1-3	
A	PATENT ABSTRACTS OF vol. 1999, no. 05, 31 May 1999 (1999-0 & JP 11 029828 A (S 2 February 1999 (19 * abstract *	5-31) ONY CORP),	1-3	TECHNICAL FIELDS SEARCHED (Int.CI.7) B29B C08J C22B
·1.	The present search report has t			
	MUNICH	Date of completion of the search 30 July 2002	Kofo	ed. J
X : partic Y : partic docus A : techr	CEGORY OF CITED DOCUMENTS Cularly relevant if taken alone cularly relevant if combined with another ment of the same category clogical background written disclosure	T: theory or principl E: earlier patent do after the filing da er D: document died I L: document died f	e underlying the in current, but publis te n the application or other reasons	vention

EP 1 273 414 A1

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 02 01 3230

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

30-07-2002

	Patent docume cited in search re		Publication date		Patent family member(s)	•	Publication date
DE	4324830	Α	26-01-1995	DE	4324830 A	1	26-01-1995
US	4828661	Α	09-05-1989	DE	3732177 A	1	06-04-1989
				AU	2249388 A		06-04-1989
				CA	1328842 A		26-04-1994
				FR-	2621051 A		31-03-1989
				GB	2210386 A		07-06-1989
				ĪT	1223837 B		29-09-1990
	•			ZA	8807133 A		28-06-1989
US	5151452	Α	29-09-1992	DE	4039024 A	 1	26-03-1992
				DE	59105846 D	1	03-08-1995
				EP	0476475 A	1	25-03-1992
				ES	2073633 T	3	16-08-1995
				HK	38197 A	_	04-04-1997
				JP	2509026 B	2	19-06-1996
				ĴΡ	4305414 A	_	28-10-1992
DE	4306348	Α	25-08-1994	DE	4306348 A	1	25-08-1994
JP	11029828	A	02-02-1999	CN	1208922 A		24-02-1999
				TW	397697 B		11-07-2000
				us	6066229 A		23-05-2000
				·			